

Typical Properties of Polypropylene

General Properties	English Units	SI Units
CAS Number	9003-07-0	9003-07-0
Density	11.5 – 11.8 lbs/in ³	0.898-0.920 g/cm ³
Melt Density	9.5 lbs/in ³	0.739 g/cm ³
Bulk Density		
Pellets	31 – 43 lbs/ft ³	497 - 529 kg/m ³
Flake	30 – 32 lbs/ft ³	481 – 513 kg/m ³
Permeability Coefficients:		
Water (@25 °C)	6.0x10 ⁻⁹ in ² /sec ² -atm	5.1x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Oxygen (@ 30 °C)	2.7x10 ⁻⁹ in ² /sec ² -atm	2.3x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Carbon Dioxide (@30 °C)	10.8x10 ⁻⁹ in ² /sec ² -atm	3.5x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Hydrogen (@ 20 °C)	48.3x10 ⁻⁹ in ² /sec ² -atm	41.0x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Nitrogen (@30 °C)	0.52x10 ⁻⁹ in ² /sec ² -atm	0.27x10 ⁻¹⁰ cm ² /(sec-cm Hg)
Water Absorption @24 h Immersion	0.03%	0.03%
Mechanical Properties		
Modulus of Elasticity (Young's Modulus)		
Homopolymer	183,000 psi	1,300 MPa
Copolymer	155,000 psi	1,100 MPa
Poisson's Ratio	0.45	0.45
Hardness, Shore D Scale	55 – 65	55 – 65
Coefficient of Friction	0.3	0.3
Thermal Properties		
DSC Melting Point		
Homopolymer	320 - 329 °F	160 - 165 °C
Copolymer	275 – 318 °F	135 – 159 °C
Specific Heat (@ 23 °C)		70 -80 J/°K/mol
Heat of Fusion	37.8 Btu/lb	88 kJ/kg
Thermal conductivity (solid)		
Homopolymer	0.7 (Btu in.)/(ft. ² hr °F)	0.1 W/m °K
Copolymer	0.12 – 0.17 (Btu in.)/(ft. ² hr °F)	0.8 – 1.2 W /m °K
Thermal conductivity (melt)		0.16 W/m /°K
Vicat Softening Temperature		
Homopolymer	305 °F	152 °C
Copolymer	289 – 304 °F	143 – 151 °C
Coefficient of Linear Thermal Expansion		
Homopolymer	4 - 6 x 10 ⁻⁵ in/(in °F)	8 - 10 x 10 ⁻⁵ cm/(cm °C)
Copolymer	3 - 5 x 10 ⁻⁵ in/(in °F)	6 - 9 x 10 ⁻⁵ cm/(cm °C)
Shrinkage		
Homopolymer	1.8 – 2.0 %	1.8 – 2.0 %
Copolymer	1.5 – 1.9 %	1.5 – 1.9 %

Typical Properties of Polypropylene

Flammability Properties	English Units	SI Units
Auto-ignition Temperature	>650 °F	>340 °C
Energy Required for Ignition		>2,500 kJ/m ²
Ignition Temperature – Cloud	790 °F	420 °C
Minimum Radiant Flux for Ignition		20 kW/m ²
Smoke Specific Extension Area	1,855 – 3,320 ft ² /lb.	380 – 610 m ² /kg
Soot Yield	0.06–0.09 lbs. soot/lb	0.06–0.09 lbs. soot/kg
Electrical Properties		
Volume Resistivity		>10 ¹⁶ Ohm-cm
Conductivity		1 – 3 mhos/cm
Dielectric Constant @ 1MHz	2.1 – 2.3	2.1 – 2.3
Dielectric Strength	500 – 600 Volts/mil	0.23 – 0.25 V/cm
Power Factor		300 Hz
Dissipation Factor		
@ 10 kHz	<0.0005 h	<0.0005 h
@ 1 MHz	<0.0005 h	<0.0005 h
@ 1 GHz	<0.0005 – 0.002 h	<0.0005 – 0.002 h
Arc Resistance	136 – 185 s	136 – 185 s

Data gathered from numerous literature sources over a number of years and is presented as obtained with no guarantees as to the accuracy of the data. Unless otherwise noted, all properties are those of the bulk material at ambient room temperature.

Product inquiries:

Marina View Headquarters
 2600 South Shore Blvd.
 League City, Texas 77573
 Telephone: 281-535-6600
 Fax: 281-535-6764
 Customer Service: 800-527-5419

Battleground Manufacturing Complex
 1230 Battleground Road
 La Porte, Texas 77571
 Telephone: 713-307-3000
 Fax: 713-307-3521
 Technical Center: 800-338-0489

www.innovene.com
www.innovene.com/orders
www.innovene.com/technicalservice

Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Ineos Olefins & Polymers USA makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA. To the best of our knowledge, the information contained herein is accurate. However, neither INEOS Olefins & Polymers USA, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Any "Properties" and/or "Applications" listed in this document are not specifications. They are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED.

The name INEOS Olefins & Polymers USA and its logo are trademarks of INEOS USA LLC or its affiliated companies. June 2006 © 2006 INEOS Olefins & Polymers USA

INEOS
Olefins & Polymers USA