

R01C-01 Polypropylene Random Copolymer

Grade R01C-01 is a low flow rate, high clarity random copolymer designed for extrusion, thermoforming and blow molding. Applications that require good see-through clarity combined with good heat resistance and refrigerator temperature impact properties can benefit from the use of grade R01C-01. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520.

Applications

- Thermoformed packaging (cups, containers, lidding)
- Extrusion blow molded containers and bottles
- Extruded sheet and profiles

Benefits

- Excellent clarity
- Excellent processability
- Good impact resistance at room and refrigerator temperatures

Typical Properties¹

Resin	Value	Method
Melt Flow Rate, 2.16 kg at 230°C, g/10 min	2.0	D1238
Injection Molded Sample		
Tensile Properties at 23°C		D638
Strength at Yield, psi (MPa)	4,040 (27.8)	
Elongation at yield, %	13.8	
Flexural Modulus, 23°C, kpsi (MPa)		D790
Condition A (test speed 0.05'/min)	130(900)	
Condition B (test speed 0.5'/min)	171(1180)	
Heat Deflection Temperature at 66 psi, (455 kPa), °F (°C)	169(76.1)	D648
Izod Impact Strength, 1/8" (3 mm) notched bar, ft-lb/in (J/m)		D256
Room Temperature	9.6(512)- partial failure	
4°C (refrigerator temperature)	5.6(302)-partial failure	
Haze, at 23°C, 50-mil (1.3mm) plaque, % Transmittance	14.4	D1003
Gloss, at 60° angle	94.8	D2457

¹Typical properties will vary within specification limits.

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name Ineos Olefins & Polymers USA and its logo are trademarks of Ineos USA LLC or its affiliated companies. June 2006 © 2006 Ineos Olefins & Polymers USA

2600 South Shore Boulevard
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA



R01C-01 Polypropylene Random Copolymer

Regulatory Information

The product and uses described herein may require global product registrations and notifications for chemical inventory listings, or for use in food contact or medical devices. For further information, call + 1-800-527-5419.

Health and Safety Information

The product described herein may require precautions in handling and use because of toxicity, flammability, or other consideration. The Material Safety Data Sheet (MSDS) contains the available product health and safety information for this material and can be found at www.ineos-op.com. Before using any material, a customer is advised to consult the MSDS for the product under consideration for use.

The Material Safety Data Sheet for this product contains shipping descriptions and should be consulted, before transportation, as a reference in determining the proper shipping description. If the material shipped by INEOS O&P is altered or modified, different shipping descriptions may apply and the MSDS of the original material should not be used.

For additional information, samples, pricing and availability, please contact:

INEOS Olefins & Polymers, USA

Marina View Building
2600 South Shore Boulevard
League City, Texas 77573
Phone: +1 281 535 6600
Fax: +1 281 535 6764
Customer Service: +1 800 527 5419
Tech Service: +1 800 338 0489
www.ineos-op.com

Technical information contained herein is furnished without charge or obligation and is given and accepted at recipient's sole risk. As conditions of use may vary and are beyond the control of INEOS Olefins & Polymers USA, no representations or warranty, express or implied, are made with respect to the accuracy, reliability, or completeness of the this information. This information in no way modifies, amends, enlarges, or creates any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE HEREBY EXCLUDED. INEOS Olefins & Polymers USA shall not be responsible for any damage or injury resulting from abnormal use, from any failure to follow appropriate practices, or from hazards inherent in the nature of the product and/or material, nor for toxicological effects or Industrial Hygiene associated with particular use of any product described herein. This information relates only to the specific product and/or material designated and may not be valid for such product and/or material used in combination with any other product and/or material or in any process, unless otherwise specified. This information shall not be construed as a recommendation for any use that may infringe any patent, trademark, or the like, or as an endorsement of any material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA.

The name Ineos Olefins & Polymers USA and its logo are trademarks of Ineos USA LLC or its affiliated companies. June 2006 © 2006 Ineos Olefins & Polymers USA

2600 South Shore Boulevard
League City, TX 77573
Tel: 281-535-6600
www.ineos-op.com

INEOS
Olefins & Polymers USA