

# Typical Engineering Properties of High Density Polyethylene

General Properties	English Units	SI Units
CAS Number	25213-02-9	25213-02-9
Molecular Weight	0.062 lbs	28.0 g
Density	58.1 - 60.2 lbs/ft <sup>3</sup>	0.930-0.965 g/cm <sup>3</sup>
Melt Density	47.7 lbs/ft <sup>3</sup>	0.764 g/cm <sup>3</sup>
Bulk Density		
Pellets	36 – 40 lbs/ft <sup>3</sup>	577 - 640 kg/m <sup>3</sup>
Flake	31 – 35 lbs/ft <sup>3</sup>	497 – 561 kg/m <sup>3</sup>
Permeability Coefficients:		
Water (@ 25°C)	1.7x10 <sup>-12</sup> in <sup>2</sup> /sec <sup>2</sup> -atm	1.3x10 <sup>-10</sup> cm <sup>2</sup> /(sec-cm Hg)
Oxygen (@ 30°C)	1.4x10 <sup>-12</sup> in <sup>2</sup> /sec <sup>2</sup> -atm	1.06x10 <sup>-10</sup> cm <sup>2</sup> /(sec-cm Hg)
Carbon Dioxide (@ 30°C)	4.6x10 <sup>-12</sup> in <sup>2</sup> /sec <sup>2</sup> -atm	3.5x10 <sup>-10</sup> cm <sup>2</sup> /(sec-cm Hg)
Nitrogen (@ 30°C)	0.35x10 <sup>-12</sup> in <sup>2</sup> /sec <sup>2</sup> -atm	0.27x10 <sup>-10</sup> cm <sup>2</sup> /(sec-cm Hg)
Water Absorption @ 24 h Immersion	0.03%	0.03%
Mechanical Properties		
Modulus of Elasticity (Young's Modulus)		
Homopolymer	150,000 psi	1,035 N/mm <sup>2</sup>
Copolymer	60,000 – 145,000 psi	400 – 1,000 N/mm <sup>2</sup>
Poisson's Ratio	0.5	0.5
Hardness, Shore D Scale	55 – 70	55 – 70
Coefficient of Friction	0.29	0.29
Thermal Properties		
DSC Melting Point		
Homopolymer	275 °F	135 °C
Copolymer	230 – 273 °F	110 – 134 °C
Specific Heat (@ 23°C)		2.25 kJ/kg °K
Heat of Fusion		
Homopolymer		245 kJ/kg
Copolymer		140 – 232 kJ/kg
Thermal conductivity		
Homopolymer		0.49 W / m °K
Copolymer		0.40 – 0.47 W / m °K
Vicat Softening Temperature		
Homopolymer	270 °F	132 °C
Copolymer	233 – 266 °F	112 – 130 °C
Coefficient of Linear Thermal		
Expansion	12 x 10 <sup>-5</sup> in/(in °F)	12 x 10 <sup>-5</sup> cm/(cm °C)
Shrinkage	0.018 -0.020 in/in	0.018 – 0.020 cm/cm

# Typical Engineering Properties of High Density Polyethylene

Flammability Properties	English Units	SI Units
Auto-ignition Temperature	>650 °F	>340 °C
Energy Required for Ignition		>2,500 kJ/m <sup>2</sup>
Fuel Value Content	19,900 BTU/lb.	
Ignition Temperature – Cloud	790 °F	420 °C
Minimum Radiant Flux for Ignition		20 kW/m <sup>2</sup>
Smoke Specific Extension Area	1,855 – 3,320 ft <sup>2</sup> /lb.	380 – 610 m <sup>2</sup> /kg
Soot Yield	0.06–0.09 lbs. soot/lb polymer	0.03–0.04 kg soot/kg polymer
Electrical Properties	English Units	SI Units
Volume Resistivity	6 x 10 <sup>5</sup> Ohm-cm	6 x 10 <sup>5</sup> Ohm-cm
Dielectric Constant	2.30 – 2.32 x 10 <sup>5</sup> Hertz	2.1 – 2.3 x 10 <sup>5</sup> Hertz
Dielectric Strength	600 – 700 Volts/mil	600 – 700 Volts/mil
Power Factor	<0.0001 kHz	<0.0001 kHz
Dissipation Factor		
@ 10 kHz	<0.0005 h	<0.0005 h
@ 1 MHz	<0.0005 h	<0.0005 h
@ 1 GHz	<0.0005 – 0.002 h	<0.0005 – 0.002 h
Arc Resistance	136 – 185 s	136 – 185 s

**Data gathered from numerous literature sources over a number of years and is presented as obtained with no guarantees as to the accuracy of the data. Unless otherwise noted, all properties are those of the bulk material at ambient temperature.**

**Product inquiries:**

**Marina View Headquarters**  
 2600 South Shore Blvd.  
 Suite 500  
 League City, Texas 77573  
*Telephone:* 281-535-6600  
*Fax:* 281-535-6764  
*Customer Service:* 800-527-5419

**Battleground Manufacturing Complex**  
 1230 Independence Parkway South  
 La Porte, Texas 77571  
*Telephone:* 713-307-3000  
*Fax:* 713-307-3521  
 Technical Center: 800-338-0489

[www.ineos-op.com](http://www.ineos-op.com)

[www.innovene.com/orders](http://www.innovene.com/orders)

Technical information contained herein is furnished without charge or obligation, and is given and accepted at recipient's sole risk. Because conditions of use may vary and are beyond our control, Ineos Olefins & Polymers USA makes no representation about, and is not responsible or liable for the accuracy or reliability of data, nor for toxicological effects or Industrial Hygiene requirements associated with particular uses of any product described herein. Nothing contained in this document shall be considered a recommendation for any use that may infringe patent rights, or an endorsement of any particular material, equipment, service, or other item not supplied by INEOS Olefins & Polymers USA. To the best of our knowledge, the information contained herein is accurate. However, neither INEOS Olefins & Polymers USA, nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of the information contained herein. Any "Properties" and/or "Applications" listed in this document are not specifications. They are provided as information only and in no way modify, amend, enlarge, or create any specification or warranty, and ALL WARRANTIES, EXPRESS OR IMPLIED, INCLUDING WITHOUT LIMITATION THE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, ARE EXCLUDED.

The name INEOS Olefins & Polymers USA and its logo are trademarks of INEOS USA LLC or its affiliated companies. Nov. 2009 © INEOS Olefins & Polymers USA

**INEOS**  
**Olefins & Polymers USA**